

BOOKBINDING HOT MELT

SW6030

Application: The go-to option for the spine bonding of softcover books, textbooks and for all standard offset paper qualities.

Characteristics: Provide excellent flexibility and bonding strength; fast drying time, suitable for a wide range of machine speeds.

Specification:

Polymer basis	Ethylene vinyl acetate
Viscosity at 160 °c (mPa s)	5,000 - 6,000
Softening point	90 - 95 °c
Supply form	White opaque in granule
Application temperature	150 - 180 °c

Packaging & Storage: in 25 kg kraft bag. 40 bags/ pallet
Shelf life of 24 months, in original package, cool and dry (15-35°C).

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.