

# MATTRESS INNERSPRING

# SW1085

**Application:** For innerspring assembly in the manufacture of mattress.

**Characteristics:** Provide excellent adhesion to PP, PE non-woven, good sprayability, fast drying, and an odor-free formula.

**Specification:**

Polymer basis	Ethylene vinyl acetate
Viscosity at 160 °c (mPa s)	2,500 - 3,500
Softening point (ring & ball)	90 - 100°c
Setting time at 25 °c (sec)	approx. 5.0
Supply form	Yellow/ clear transparent
Application temperature	150 - 170 °c

**Packaging & Storage:** in 25 kg kraft bag. 40 bags/ pallet  
Shelf life of 24 months, in original package, cool and dry (15-35°C).

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.