

VENEER JOINT HOT MELT

SW8083

Application: For veneer splicing joint in the manufacturing of plywood

Characteristics: Good joint quality with polyester yarn, good machinability, fast setting, suitable for various thickness of veneer sheets.

Specification:

Polymer basis	Ethylene-Vinyl Acetate
Viscosity at 140 °c (mPa s)	35,000 - 45,000
Softening point	90-100 °c
Open time	5 secs.
Application temperature	150 - 170 °c

General guidance: For best bonding results, the materials to be used must be free of dust, oil, and grease, and be dry.

Packaging: 25 kg net weight, in non-woven bag

Storage: 24 months, in original package, cool and dry (15-35°C).

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.