

**EDGE BANDING HOT MELT**

**SW826L**

**Application:** Cost-performance option for automatic machines, suitable for a variety of edgebands including PVC, ABS, paper, and veneer.

**Characteristics:** Provide a good balance of cost and performance, with excellent adhesion and durability, suitable for a wide range of machine speeds

**Specification:**

Polymer basis	Ethylene-Vinyl Acetate
Viscosity at 200 °c (mPa s)	50,000 - 60,000
Softening point	90 - 100 °c
Supply form	Opaque white in granule
Application temperature	180 - 210 °c

**General guidance:** For best bonding results, the materials to be used must be free of dust, oil, and grease, and be dry.

**Packaging:** 25 kg net weight, in non-woven bag

**Storage:** 24 months, in original package, cool and dry (15-35°C).

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.