

PROFILE WRAPPING HOT MELT

SW8630A

Application: For wrapping profiles and frames made of solid wood, particleboard or MDF, with veneer and CPL.

Characteristics: Provide superior bonding & good heat/solvent resistance. Clear melting with an odor-free formula.

Specification:

Polymer basis	Ethylene-Vinyl Acetate
Viscosity at 180 °c (mPa s)	15,000 - 20,000
Softening point	80 - 90 °c
Supply form	Clear transparent in granule
Application temperature	180 - 210 °c
Process	roller applicators

Packaging: 25 kg net weight, in non-woven bag

Storage: 24 months, in original package, cool and dry (15-35°C).

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.