

MEMBRANE PRESSING

SW3191

Application: For the pressing of veneer panels, with PVC in the manufacture of interior and cabinet doors.

Characteristics: It bonds extremely well to vinyl films and particle-board or MDF, offering good water and heat resistance.

Specification:

Polymer basis	Polyurethane
Viscosity at 25 °c (mPa s)	1,800 - 2,000
Solid content	50 +/- 2%
Supply form	white emulsion
Process temperature	room temp.

Direction for use: The adhesive can be used as it is. Also can be used with a curing agent. Adding 2-5% of the curing agent. Mix evenly and spray. (Use up within 8 hours)

Packaging & Storage: in 20 kg plastic drum. 24 drums/ pallet
Shelf life of 9 months, in original package, cool and dry (15-35°C).

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.