

**EDGE BANDING HOT MELT**

**SW8062A**

**Application:** Unfilled. Featured option for manual machines and contour edge-banding, with low process temperature.

**Characteristics:** Provide excellent adhesion and high yield with clear melting and good oxidation stability.

**Specification:**

Polymer basis	Ethylene-VInyl Acetate
Viscosity at 180°C (mPa s)	9,000 - 10,000
Softening point	85-95 °c
Supply form	Transparent yellow in granule
Application temperature	120 - 150 °c

**General guidance:** For best bonding results, the materials to be used must be free of dust, oil, and grease, and be dry.

**Packaging:** 25 kg net weight, in non-woven bag

**Storage:** 24 months, in original package, cool and dry (15-35°C).

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.