

## REACTIVE PUR EDGE BANDING

## PUR6818

**Application:** 100% single-component moisture-cured polyurethane hot melts, designed for all kinds of automatic edgebanders with PUR applicator.

**Characteristics:** Processing from moisture-proof sealed drums, our Reactive Polyurethane (PUR) offers good initial and ultimate adhesion with moderate open time, makes it suitable for different environments.

**Specification:**

Polymer basis	Polyurethane
Viscosity at 120°C (mPa s)	40,000 - 60,000
Complete curing time	48 hours
Supply form	Natural white color block-shaped
Application temperature	120 - 150°C

**Packaging & Storage:** 20 kg steel drums with aluminum sealing. 24 drums/ pallet; Shelf life of 12 months, in original package, cool and dry (15-35°C).

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.